


INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: E01C 13/08	A1	(11) International Publication Number: WO 98/56993 (43) International Publication Date: 17 December 1998 (17.12.98)
(21) International Application Number: PCT/CA98/00559 (22) International Filing Date: 9 June 1998 (09.06.98) (30) Priority Data: 2,206,295 9 June 1997 (09.06.97) CA (71) Applicant (for all designated States except US): 2752-3273 QUEBEC INC. [CA/CA]; Suite 2900, 1000 de la Gauchetiere, Montreal, Quebec H3B 4W5 (CA). (72) Inventor; and (75) Inventor/Applicant (for US only): LEMIEUX, Alain [CA/CA]; 1360 Cherbourg Street, Sherbrooke, Quebec J1K 2P2 (CA). (74) Agent: MacRAE & CO.; P.O. Box 806, Station "B", Ottawa, Ontario K1P 5T4 (CA).	(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>	

(54) Title: SYNTHETIC TURF GAME SURFACE**(57) Abstract**

A synthetic turf surface for golf courses, tennis courts and other grass-surfaced game playing fields is formed of a synthetic grass carpet having a flexible base sheet (14) with closely spaced-apart upright, blade-like strands (12) of plastic material forming a dense grass-like surface. The carpet is supported upon a cushioning underpad (18) which is formed of a thick, molded sheet of open cell, expanded bead polypropylene. The resiliently compressible polypropylene underpad combined with the synthetic grass carpet closely simulates the feel of a natural grass covered playing surface.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

- 1 -

SYNTHETIC TURF GAME SURFACE

TECHNICAL FIELD

This invention relates to an improved synthetic turf surface for grass-type game playing fields.

5

BACKGROUND OF INVENTION

Synthetic turf game playing surfaces typically are formed of carpets having upright piles or strands that are fastened to a base or backing sheet. The strands may be formed of thin, flat, narrow strips of suitable plastic material which may be gathered into tufts that are fastened to the base sheet. Commonly, the base sheet
10 is formed of a woven cloth, made of a suitable plastic fabric, with a resilient coating or binder applied to the base sheet for anchoring the strands thereto. The detailed construction of such pile carpets varied considerably. However, in general, they are made of a weather resistant or outdoor type of construction.

Such carpets are usually laid upon a prepared, flat ground surface to form a
15 game playing field which is intended to simulate a natural grass playing field surface. For some types of games, a resilient underpad is placed beneath the carpet and upon the firm ground support surface to provide a shock absorbing effect. Also, in some instances, a layer of sand or other particulate material is placed upon the upper surface of the carpet base sheet and around the strands. An example of this type of
20 construction is shown in U.S. Patent No. 4,389,435 issued June 21, 1983 to Frederick T. Haas, Jr. Another example is shown in U.S. Patent No. 4,637,942 issued January 20, 1987 to Seymour A. Tomarin.

Further, examples of artificial turfs which are formed with the grass-like carpet placed upon a resilient underpad are disclosed in U.S. Patent No. 3,551,263 issued
25 December 29, 1970 to Carter et al., which discloses a polyurethane foam underpad; U.S. Patent No. 3,332,828 issued July 25, 1967 to Faria et al., which discloses a PVC foam plastic or polyurethane foam plastic underpad; U.S. Patent No. 4,637,942 issued January 20, 1987 to Seymour A. Tomarin which discloses a rubber-like underpad; U.S. Patent No. 4,882,208 issued November 21, 1989 to Hans-Urich Brietschdel,
30 which illustrates a closed cell polyethylene foam underpad; U.S. Patent No. 3,597,297 issued August 3, 1971 to Theodore Buchholz et al., which discloses a polyurethane underpad having voids; and U.S. Patent No. 4,505,960 issued March 19, 1985 to

- 2 -

James W. Leffingwell, which discloses shock absorbing pads made of foamed polyvinyl chloride, polyethylene, polyurethane, polypropylene, etc.

As these various prior patents demonstrate, there has been a search in the past for an underpad material and construction which, when combined with a suitable
5 synthetic blade forming carpet, provide a game playing surface which very closely simulates the feel and action and reaction effect of a natural grass playing field surface. The large variety of materials disclosed in the foregoing patents demonstrate that such a synthetic turf playing surface had not been found.

The present invention relates to a particular plastic underpad surface
10 combined with an artificial grass forming carpet which very closely simulates a natural grass field which is particularly close in feel and performance to the natural grass portions of a typical golf course, as well as being very similar to other natural grass surface game playing fields.

SUMMARY OF INVENTION

15 This invention contemplates combining with a synthetic grass carpet a particular resilient polypropylene molded underpad which, together with the synthetic grass carpet, produces an effect which is strikingly similar to a natural grass playing surface formed particularly for golf courses. Thus, this invention contemplates utilizing expanded beads of polypropylene of a density of approximately between
20 about 1.3 to 2.8 pounds per cubic foot molded into a thick sheet or pad of open cell structure with a density of between about 1.5 to 3 pounds per cubic foot. The combined turf carpet and supporting underpad effect may be enhanced by treating the free ends of the synthetic grass blades with a sandblast which splits or shreds the blade ends into fine slivers which intertwine and entangle with each other to form a
25 dense mat upper surface upon the carpet.

An object of this invention is to provide an artificial turf with a particular resilient underpad formed of open cell, expanded beads polypropylene plastic which produces, as part of the turf surface, an effect which very closely simulates a natural grass playing field.

30 These and other objects and advantages of this invention will become apparent upon reading the following description, of which the attached drawings form a part.

DESCRIPTION OF DRAWINGS

FIG. 1 is a schematic, fragmentary, cross-sectional end view of a synthetic turf
35 pile carpet.

- 3 -

FIG. 2 is a schematic view similar to FIG. 1, showing the carpet positioned upon a resilient, molded open cell, expanded bead polypropylene underpad.

FIG. 3 is a view, similar to FIG. 2, illustrating the step of sandblasting the upper end portions of the blade forming strands of the carpet.

5 FIG. 4 schematically illustrates the artificial turf surface with the dense mat formed by the shredded slivers and with a layer of sand deposited by the sandblasting step upon the upper surface of the carpet base sheet.

FIG. 5 schematically illustrates a further, optional, step of spraying the carpet with a water wash for further severing the slivers on a strand while additionally
10 entangling or intertwining adjacent slivers to form the dense mat surface and, also, a rotary brush treating the upper surface of the mat.

FIG. 6 schematically illustrates a single U-shaped strand whose free upper ends have been shredded into fine slivers by the sandblasting treatment.

FIG. 7 schematically illustrates a fragmentary portion of a golf course where
15 the golfer may use a Tee.

FIG. 8 is an enlarged, fragmentary, schematic, cross-sectional view showing a Tee inserted in a slot provided in artificial turf which has a mat formed on its upper surface.

FIG. 9 is a view similar to FIG. 8 showing a Tee inserted in a slot formed in
20 turf which is not formed with upper end slivers and a matted surface.

DETAILED DESCRIPTION

FIG. 1 schematically illustrates a fragment of a synthetic turf pile carpet. The carpet has numerous, closely spaced, tufts 11 which are formed of U-shaped, flat, narrow bent strips or strands 12 that form artificial grass blades. The turfs are
25 fastened upon a base or backing sheet 14. This sheet may be made of a woven cloth or the like fabric material formed of stable, weather resistant, plastic such as polypropylene or nylon fibers or the like. The specific cloth must be flexible but, otherwise, may vary as to its composition.

As schematically illustrated in FIG. 1, the tufts are inserted around or through
30 the fibers forming the base sheet. A suitable binder layer 16 may be applied to bind the turfs and base sheet together. The binder may be formed of a polyurethane adhesive material or some other suitable, outdoor usable adhesive which remains resilient or flexible.

The carpet is placed upon a resilient cushion underpad 18. This underpad is
35 formed of a relatively thick, molded sheet or pad of resilient, open cell, expanded

- 4 -

bead polypropylene. The sheet may be approximately between about 1/2 inch to 2 inches in thickness, with a preferred density of approximately 2.36 pounds per cubic foot. The density may be varied within the range of between about 1.5 to 3 pounds per cubic foot. The thickness of the pad, depending upon the particular results
5 desired, may also be varied from about 1/4 inch thickness to as much as up to 12 inches thick.

With the carpet positioned upon the resilient cushion underpad 18, the upper portions of the strands or blades are sprayed with a blast of sand 20 or similar sand-like particulate material from a pressurized nozzle 21. This blast of sand shreds each
10 of the strand upper end portions into numerous slivers 23 (see FIG. 6). The slivers extend laterally and intertwine and entangle together to form a dense mat 24.

The spray nozzle 21 may be moved back and forth from one side to the other in a scanner-like movement across the upper end portions of the blades formed by the strands. The exact pressure of the sand blast spray may be varied. However,
15 a preferred blast pressure is in the range of 100 to 120 pounds per square inch. The blast may use silica sand of a size range of between about 16 to 40 mesh and, preferably, in the range of between about 20 to 24 mesh or even more preferably in the approximate area of 24 mesh. The sandblasting is conducted at a speed of movement and for a length of time which is sufficient to shred the strand end portions
20 into finely divided slivers. For example, the upper, about one-fifth portions of the blades may be shredded into fine slivers that remain attached to their respective blades.

The force of the sand blast, depending upon how long, that is, how slowly the blast is moved across the surface of the carpet, not only shreds the blades, but also
25 forces the sprayed sand downwardly between the strands to deposit sand upon the surface of the base sheet of the carpet. The sand layer 25 formed thereby may be kept upon the base sheet of the carpet where it is maintained in position by the dense intertwined or entangled sliver mat formed on the upper ends of the blades.

By way of example, a blade height of approximately 5/8 of an inch above the
30 surface of the base sheet, which is useful for a golf green surface may have its upper 20 to 33 percent of its length shredded into fine slivers. In this example, strands which are approximately 1/16 of an inch, i.e. about 0.07 inches, wide and about 0.002 inches thick, so that they are approximately rectangular in cross-section. They are bent in half, to form two blades, and are gathered into tufts of about 9 to 11 strands.
35 These form about 18 to 22 blades per tuft. The upper about 20 percent portions of

- 5 -

each blade may be severed into about four slivers. Thus, each tuft may have as many as about 70 to 80 slivers whose lower ends remain attached to the blade body and whose upper ends extend off into transverse directions to entangle with the slivers of adjacent strands. The slivers are about 0.02 inches in width and about
5 0.075 to 0.125 inches long.

Following the sandblasting step, the carpet may be further treated with a high pressure water spray 27 applied by a pressurized nozzle 28. The water spray, which, for example, could be at a roughly 100 to 150 pounds per square inch nozzle pressure, acts like a wash which further separates adjacent slivers that were
10 shredded, but not fully separated from each other on the same strand, and simultaneously further twists, bends and entangles the slivers of one strand with slivers on its adjacent strand to further densify the mat formed by the intertwined slivers. This forms a denser and more uniform mat surface.

The mat surface may be further treated by brushing it with, for example, a
15 rotary brush 29 applied upon the mat surface to make the mat surface more uniform. The water jet and the brushing may be performed successively or at the same time as schematically illustrated in FIG. 5.

Significantly, the force of the sandblasting is sufficiently absorbed through the resilient cushioning pad beneath the carpet to prevent the strands from becoming
20 crushed or permanently deformed or compacted by such force. That is, the strands remain or return to their upright positions after their upper ends are sand blasted. The upright positions are maintained, in part, by the deposited sand layer 25. Similarly, the strands and the mat 24 hold the sand layer 25 in place.

The sand layer filling may be kept in place and the matted carpet may be
25 rolled and transported to the site where it is to be spread and used with the sand layer. This permits the sand blast treatment to be performed either on the site of the game playing field or at any work site or factory area where the application of the sand, water and brushing treatments may be more conveniently performed. Thus, the treated carpet may be unrolled and installed at the game surface site when desired
30 and the sand layer will remain in place and additional sand at the use site for a sand filling may not be needed.

As mentioned, the particular pile carpet construction may be varied. However, an example of a useful carpet for a golf green comprises synthetic grass of approximately 7,600 deniers, an approximate density of 42 ounces per square yard,

- 6 -

and a fiber height of approximately 5/8 inch combined with an underpad of 1/2 inch to 2 inches in thickness.

Similarly, an example of a fairway portion of a golf course may be in the range of approximately 7,600 deniers synthetic grass, an approximate density of 42 to 55 ounces per square yard, with a fiber height of about 5/8 to 2 inches with an underpad of at least about one inch thick.

Still another example of the synthetic grass would be a weaving standard in the range of 3,600 to 10,000 deniers, with 13 to 22 stitches per 3 inches, 3/16 gage and a density of about 34 to 65 ounces per square yard of material.

10 The raw beaded polypropylene material is commercially available and can be molded into underpads of the desired density. By way of example, expanded polypropylene beads are available from BASF under the trade name of NEOPOLEN P, which is a trademark of BASF. This material is available at densities of 1.3, 1.9 and 2.8 pounds per cubic foot and is referenced by BASF by its trademark EPERAN
15 PP, types PP45, PP30 and LBS 20. When the beads are molded in appropriate slab molding equipment at times and pressures known to those skilled in the art, the resulting pad, produced in the desired thickness, can be made in a density ranging from 1.5 to 3 pounds per cubic foot. The molded slab or sheet will have an open cell construction. The specific density selected may be varied for specific sport activities.
20 For example, a density that has been found satisfactory for a golf green is in the range of approximately 2.36 pounds per cubic foot.

The particular technique useful for the sandblast treatment involves sandblasting under pressure using commercially available sandblast equipment. A pressure in the range of 100 to 120 pounds per square inch is preferred but the
25 pressure may be varied somewhat, such as a low of about 80 pounds per square inch. By moving the spray nozzle in back and forth movements across the surface of the carpet, the projected spray is sequentially concentrated upon small portions of the carpet. The angle of the projected spray may vary but a preferred angle, which appears to be effective in a minimum of time, is an angle of about 70 to 80 degrees
30 relative to the plane of the carpet. The distance of the nozzle from the strands may vary, with the equipment operator selecting the optimum distance by visually observing the shredding action of the spray. An example of the distance may be in the range of about 4 to 5 feet, depending upon the speed of movement of the nozzle across the carpet.

- 7 -

The resulting synthetic turf is particularly useful for golf courses, such as the green portions, approach portions, Tee-off portions and fairway. The turf surface also may be used for tennis courts, football or soccer as well as for other sports which utilize grass surfaces. Examples of these are grass hockey, croquet, grass bowling, children playground, baseball, and the like. The surface of the artificial turf produced by the method herein, closely simulates the feel and action or rebound produced by a natural grass surfaced playing field. The completed, matted surface very closely simulates the natural grass surfaces required for golf courses and the similar playing fields. This turf may also be useful upon a rooftop or patio or deck surface where the turf will provide an insulated, waterproof covering.

As illustrated in FIGS. 7 and 9, the turf may be used on golf courses in Tee-off places, that is, at locations where the golfer uses a Tee to support the ball for a drive. In those locations, a number of slits 30 may be made in the turf carpet base sheet and underpad to receive a manually inserted standard Tee. The slits 30 may be of a size to closely receive a Tee 31. To assist the golfer in locating a particular slit, a colored mark 32 may be applied, as by a suitable ink or paint mark, on the surface of the turf. FIG. 7 shows the turf with the sliver forming mat and FIG. 8 shows the turf mold without the surface mat. In either case the slots can be used to receive the golfer's Tee.

This invention may be further developed within the scope of the following claims. Accordingly, it is desired that the foregoing description be read as being merely illustrative of an operative embodiment of this invention and not in a strictly limiting sense.

- 8 -

CLAIMS

1. A synthetic turf surface for golf and other grass-type game playing surfaces formed of a synthetic grass carpet having a flexible base sheet with closely spaced apart, upright blade-like strands of plastic material secured to the sheet, and
5 with the strands forming a densely packed, exposed upper surface and said base sheet being positioned upon a resilient cushion underpad arranged upon a firm support surface, the improvement comprising:
said underpad being formed of a relatively thick sheet of a molded, open cell, expanded, resilient polypropylene bead material;
10 whereas said carpet and its supporting underpad closely simulate a portion of a natural grass golf course surface, such as a green or tee-off or fairway portion and similar grass-type playing surfaces.
2. A synthetic turf surface as defined in claim 1 and said polypropylene beads being of density of between about 1.3 to 2.8 pounds per cubic foot and said
15 underpad being of a thickness of between about 1/4 inch to 12 inches.
3. A synthetic turf surface as defined in claim 2 and said polypropylene material being of a density of approximately between about 1.3 and 1.9 pounds per cubic foot and a thickness of approximately between about 1 inch to 2 inches whereby the surface forms a simulated natural golf green or a tee-off portion of a golf course.
- 20 4. A synthetic turf surface as defined in claim 2 and with the density of said polypropylene material being approximately 1.9 pounds per cubic foot and of a thickness of approximately between about 1/2 inch to 1 inch thickness to form a simulated natural grass tennis court playing surface.
- 25 5. A synthetic turf surface as defined in claim 2 and with the density of said polypropylene material being approximately 1.3 pounds per cubic foot and said underpad being approximately between about 1 to 2 inches thick to form a simulated natural golf surface tee-off portion.

- 9 -

6. A synthetic turf surface as defined in claim 2 and with the density of said polypropylene material being in the range of approximately 1.9 pounds per cubic foot and the thickness of the underpad being approximately between about 1 to 2 inches, to form a simulated natural golf green surface.







5 7. A synthetic turf surface as defined in claim 1 and said underpad being molded of expanded polypropylene beads of approximately between about 1.3 to 2.8 pounds per cubic foot density and approximately between about 1/2 inch to 2 inches thickness, molded into a unitary, open cell, pad of a density of approximately between about 1.5 to 3 pounds per cubic foot.

10 8. A synthetic turf surface as defined in claim 7 and with the density of said molded underpad being approximately 2.36 pounds per cubic foot to form a simulated natural golf green or the like portion of a golf course surface.

9. A synthetic turf surface as defined in claim 1 and including the upper end portions of said strands being shredded into fine slivers which are densely matted and intertwined, and with a layer of sand-like particulate material applied upon the upper surface of the base sheet and generally beneath the intertwined slivers and substantially filling the interstices between the strands and said layer is covered by said intertwined slivers.

10. A synthetic turf surface as defined in claim 1 and including an adhesive-like reinforcement layer of a flexible, resilient material, applied to the lower surface of the base sheet and above the upper surface of the underpad and formed of a synthetic plastic material such as a polyurethane plastic.

11. A synthetic turf surface as defined in claim 1 and including numerous, spaced-apart, short slits formed in the carpet with the slits being of a size to temporarily receive a downwardly inserted standard size golf tee, whereby a golf player may manually insert a tee in any selected slit to support a golf ball for a drive.



2/2




Fig-7




Fig-8




Fig-9

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 E01C13/08

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 E01C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 505 960 A (LEFFINGWELL JAMES W) 19 March 1985 cited in the application see column 4, line 40 - line 46 see abstract	1
A	US 4 830 798 A (MAEDA HIROFUMI) 16 May 1989 see abstract	1
A	US 5 373 667 A (LEMIEUX ALAIN) 20 December 1994 see abstract	9

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- "&" document member of the same patent family

Date of the actual completion of the international search

28 August 1998

Date of mailing of the international search report

04/09/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Dijkstra, G

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4505960	A	19-03-1985	AU 564195 B	06-08-1987
			AU 3181284 A	14-02-1985
			CA 1229854 A	01-12-1987
			EP 0168545 A	22-01-1986
			JP 1731938 C	17-02-1993
			JP 4021582 B	10-04-1992
			JP 60071246 A	23-04-1985
US 4830798	A	16-05-1989	CA 1274662 A	02-10-1990
			DE 3777317 A	16-04-1992
			DK 483687 A	17-03-1988
			EP 0263989 A	20-04-1988
			FI 874016 A,B,	17-03-1988
			JP 8300387 A	19-11-1996
			JP 6059694 B	10-08-1994
			JP 63183832 A	29-07-1988
			KR 9510982 B	26-09-1995
US 5373667	A	20-12-1994	NO 175065 B	16-05-1994
			US 5356344 A	18-10-1994